

westcoat®


TIDALSTONE™

THIN FILM

EC

EPOXY COAT

DURABLE RESINS & HARDENERS




westcoat®

TIDALSTONE THIN FILM SUBMITTAL PACKAGE

**DIVISION 09 – FINISHES
SECTION 09 67 23 RESINOUS FLOORING**

TABLE OF CONTENTS

System Brochure	3-5
System Specification Sheet	6-11
CSI Specification	12-16
Color Chart	17-18
Sample Warranty	19-20
General Maintenance	21-23



westcoat®

SYSTEM BROCHURE



westcoat.
SPECIALTY COATING SYSTEMS

TIDALSTONE™



ABOUT TIDALSTONE™

Westcoat's Tidalstone™ Flooring System is a multi-layered flooring system that features innovative and decorative aggregate blends. The combination of ultra fine and oversized particles simulate the look of an exposed aggregate in a polished concrete surface. Replicate the look while providing all the benefits and attributes of a resinous flooring system. This system can be installed as a Thin Film or High Build assembly.



ULTRA-TOUGH. PROTECTIVE.

- USDA Compliant
- Chemical-Resistant
- Seamless
- Simulates exposed aggregate
- Endless color combinations
- Can be Installed Solvent-Free
- UV Resistant Finish



FOR PROFESSIONAL USE ONLY.



westcoat.com / 800.250.4519 / info@westcoat.com



TIDALSTONE A SIMULATED CONCRETE LOOK FOR INTERIOR FLOORS


Tidalstone™ introduces a new Texture-Coat product that can be applied in decorative and industrial solutions: TC-62 Tidalstone Aggregate Blend is a synthetic, broadcast medium that is available in seven different color blends: Cambria, Trinidad, Avalon, Mendocino, Laguna, Hermosa, and Coronado.

Tidalstone™ comes in a multitude of colors and can be applied over various topcoats, allowing for customization for every space.

THIN FILM

Westcoat's Tidalstone™ Thin Film Flooring System is the standard Tidalstone system that combines Westcoat's epoxy primer, polyaspartic topcoat, polyurethane sealer, and aggregate blend products to create a seamless, decorative floor coating. It is ideal for areas such as showrooms, offices, recreation rooms, laboratories, and more.

THIN FILM




Concrete Primer Broadcast Coat Polyaspartic Topcoats Polyurethane Sealer

HIGH BUILD

Westcoat's Tidalstone™ High Build Flooring System has all the features of Tidalstone Thin Film with the use of Westcoat's Temper-Crete™ urethane cement base instead of Epoxy Primer and Patch Gel. This provides extra benefits such as Thermal Shock Resistance, Moisture Tolerance, Self-Leveling, and High Compressive Strength.

HIGH BUILD




Concrete Temper-Crete Coat & Broadcast 2nd Broadcast Coat Polyaspartic Topcoats Polyurethane Sealer





westcoat®

SYSTEM SPECIFICATION SHEET



westcoat®

SYSTEM SPECIFICATION

EC

EPOXY COAT
DURABLE RESINS & HARDENERS

Tidalstone™ Flooring System

Thin Film


Description

Westcoat's Tidalstone™ Flooring System is a multi-layered, resinous flooring system that features the decorative TC-62 Tidalstone™ aggregate blends, EC-102 Polyaspartic and SC-65F WB Flat Clear Polyurethane Sealer. This unique system produces a finish similar to the look of polished concrete or terrazzo flooring, with a natural, flat finish, while providing all the benefits and attributes of a resinous flooring system.

Uses

Tidalstone™ Flooring System is a decorative, durable and chemical resistant option that is an ideal choice for designers and architects and is intended for use in showrooms, offices, recreation rooms, laboratories and clean rooms.

System Overview



System Data

Coverages	Primer	Broadcast Coat	Tidalstone Aggregate Blend	Polyaspartic Topcoats	WB Flat Polyurethane Sealer
	250-300 ft ² per gallon	175-225 ft ² per gallon	7-8 ft ² per pound	1st: 120-140 ft ² per gallon 2nd: 250-300 ft ² per gallon	680-720 ft ² per gallon
Components	EC-72 Epoxy Patch Gel EC-12 Epoxy Primer EC-102 Polyaspartic Topcoat SC-65F Polyurethane Sealer TC-62 Tidalstone Aggregate Blend CA-33 Aluminum Oxide #320		Shelf Life	System Thickness 30-40 mils DFT	
			2 years		
			2 years		
			2 years		
			1 year		
			N/A		
			N/A		

Advantages

USDA Compliant • Chemical Resistant • Seamless • Easy Clean Up • Durable • Decorative
• Choice of Colors • Can be Installed Solvent Free • UV Resistant Finish • Aluminum Oxide Finish

Inspection


The surface must be structurally sound, clean, dry and free of grease, paint, oil, dust, curing agents, laitance or any foreign material that will prevent proper adhesion. The concrete should be at least 2,500 PSI and porous or rough enough to allow the product to soak in. A minimum of 28 days curing time is required on all concrete. Prior to starting work, test existing concrete slab for efflorescence, moisture and hydrostatic pressure.

DISCLAIMER: PURCHASER'S SOLE AND EXCLUSIVE REMEDY AGAINST THE MANUFACTURER OF WESTCOAT, SHALL BE LIMITED SOLELY TO THE REPLACEMENT OF ANY DEFECTIVE MATERIAL OR A PAYMENT BY THE MANUFACTURER IN AN AMOUNT EQUAL TO THE COST OF THE ORIGINAL MATERIAL.



4007 Lockridge St • San Diego, CA 92102
800-250-4519 • Fax 619-255-7187 • westcoat.com

1 of 5
Tidalstone™ Thin Film 11/25

**westcoat®****SYSTEM
SPECIFICATION****EC****EPOXY COAT**
DURABLE RESINS & HARDENERS**Tidalstone™ Flooring System** Thin Film**Preparation**

Pre-cut and clean all cracks and joints with a concrete diamond blade to at least ¼ x ¼ inch. Prepare concrete to a profile equal to CSP 3 as specified by ICRI. Methods may vary according to the condition and hardness of the concrete. Other factors include the forecasted use of the surface and the environment in which it is to be installed. When preparing the surface use caution when shot blasting, scarifying too aggressively, leaving grind marks or grinding too smooth.

Moisture

All concrete should be tested for moisture before applying a seamless coating. If moisture emissions exceed 5 lbs/1000 square feet (ASTM F1869) or if the relative humidity (RH) exceeds 75% (ASTM F2170), please refer to the EC-15 Moisture Vapor Barrier Product Specification Sheet.

Crack Treatment

Mix 1 part A with 1 part B (by volume) of EC-72 Epoxy Patch Gel together for 3-4 minutes and apply to the crack using a trowel or putty knife. Patch all spalls and cracks with EC-72 and allow to dry 2-3 hours before priming. The material may be slightly overfilled in the crack and when completely dry (in 4-6 hours) can be sanded or ground smooth. This remedial approach to patch cracks is not guaranteed and it should be noted that when the substrate moves, it could likely crack the Tidalstone™ Flooring System.

Primer

It is recommended to use pigmented EC-12, in the same color as the EC-102, for a more uniform and consistent finish. Mix 2 parts A with 1 part B (by volume) of EC-12 Epoxy Primer together for 3-4 minutes. For best penetration into concrete, thin by adding 1-2 quarts of Westcoat's CA-23 to each 1½ gallon kit. Thinned material must be applied at less than 5 mils. To cure properly, do not allow product to puddle. Immediately apply at a rate of 250-300 square feet per gallon, using a trowel or squeegee and then back roll to ensure complete coverage. For best results, it is recommended to apply a second coat of EC-12, neat at 150-250 square feet per gallon, to seal the concrete and provide an even surface for the Broadcast Coat.

Broadcast Coat


Mix 1 part A and 1 part B (by volume) of EC-102 Polyaspartic (Pigmented). For color consistency, box all part A's. Apply at the rate of 175-225 square feet per gallon. Broadcast pre-mixed TC-62 Tidalstone™ aggregate blends into the wet EC-102 to refusal (until no shiny spots are evident), at approximately 7-8 square feet per pound. After the EC-102 has cured, collect all loose TC-62 and scrape and sand surface. Sanding the surface with a finer grit may provide a smoother texture when desired. Ensure that the surface is dry enough to sand, as sanding improperly may damage the surface. Vacuum all loose TC-62 and ensure that the floor is clean and free of any unbonded TC-62, prior to proceeding with the Polyaspartic Topcoat.

Polyaspartic Topcoat

Combine 1 part A, with 1 part B of EC-102 Clear Polyaspartic and mix thoroughly with a low speed drill motor for 2-3 minutes. Pour immediately onto the floor and spread the material using a squeegee or trowel. Use a ¾ inch nap, non-shedding roller cover and backroll the material in both directions. Coverage should be around 120-140 square feet per gallon. After the topcoat has dried, you may sand or scrape rough spots and apply a second coat of EC-102 Clear at approximately 250-300 square feet per gallon. If additional coats are desired, they must be applied within 24 hours or the cured material must be sanded and wiped with acetone, before application.

DISCLAIMER: PURCHASER'S SOLE AND EXCLUSIVE REMEDY AGAINST THE MANUFACTURER OF WESTCOAT, SHALL BE LIMITED SOLELY TO THE REPLACEMENT OF ANY DEFECTIVE MATERIAL OR A PAYMENT BY THE MANUFACTURER IN AN AMOUNT EQUAL TO THE COST OF THE ORIGINAL MATERIAL.

**westcoat®**4007 Lockridge St • San Diego, CA 92102
800-250-4519 • Fax 619-255-7187 • westcoat.com2 of 5
Tidalstone™ Thin Film 11/25

**westcoat®****SYSTEM
SPECIFICATION****EC****EPOXY COAT**
DURABLE RESINS & HARDENERS**Tidalstone™ Flooring System** Thin Film**WB Flat Polyurethane Sealer**

Pre-mix each component of SC-65F WB Flat Polyurethane Sealer separately. In a clean bucket, mix 3 parts A with 1 part B (by volume) of SC-65F Water-Based Flat Polyurethane Sealer. Mix thoroughly with a low speed (200-300 rpm) drill motor for 2-3 minutes. For maximum wear resistance, add ¼ to ½ pound (~2-4 oz by volume) of CA-33 #320 and mix into activated product. Make sure to scrape the sides and bottom of the container during mixing. Immediately after mixing, apply the SC-65F onto the substrate at a rate of 680-720 square feet per gallon using a "Dip and Roll" method. Back roll with a ¼ inch, high-quality, non-shedding roller cover, being sure to maintain a wet edge. For best results, two coats may be recommended to ensure an even finish. They must be applied within 24 hours or the cured material must be sanded and wiped with acetone, before application.

Dry Time

You may re-coat as soon as the surface is dry to the touch or in about 4-8 hours. Light foot traffic may be permitted in 12 hours, normal traffic in 24 hours and vehicle traffic in 72 hours. All times are based on average temperature of 72F degrees and 50% humidity. Avoid heavy abrasion and chemical exposure for 5 days.

Optional Materials**Flex Epoxy Membrane**

- When a 100% flexible epoxy membrane is required, Westcoat's Flex Epoxy System may be installed prior to installing the Tidalstone Thin Film System.

Broadcast Coat - 100% Solids Option

- When a 100% solids system is required, EC-33, EC-34, EC-36 or EC-101 can be used in lieu of EC-102 for the broadcast coat.

Cove

- Epoxy Cove System can be used to create cove at the wall to floor transition.

Topcoat - 100% Solids Option

- When a 100% solids system is required, EC-36 or EC-101 can be used in lieu of EC-102 for the Topcoat.

Topcoat Options

- EC-95G or EC-95F can be used in lieu of SC-65F, when a solvent-based polyurethane topcoat is required.
- SC-65G or SC-65SG can be used in lieu of SC-65F when a Gloss or Semi-Gloss WB Polyurethane is required.

Skid Resistance

- CA-30 Small Safe Grip or CA-31 Large Safe Grip can be added to the EC-102 to produce a skid-resistant surface.
- CA-33 Aluminum Oxide can be used for skid resistance in heavy traffic areas.

* Please refer to Product and System Specification Sheets for additional information.

DISCLAIMER: PURCHASER'S SOLE AND EXCLUSIVE REMEDY AGAINST THE MANUFACTURER OF WESTCOAT, SHALL BE LIMITED SOLELY TO THE REPLACEMENT OF ANY DEFECTIVE MATERIAL OR A PAYMENT BY THE MANUFACTURER IN AN AMOUNT EQUAL TO THE COST OF THE ORIGINAL MATERIAL.

**westcoat®**

4007 Lockridge St • San Diego, CA 92102
800-250-4519 • Fax 619-255-7187 • westcoat.com

3 of 5
Tidalstone™ Thin Film 11/25



Clean Up

Uncured material can be removed with solvent. If cured, material can only be removed mechanically or with an environmentally-safe solvent.

Maintenance

Interior Floors can be dust mopped daily or mopped using a neutral pH cleaner. For more information on floor care and maintenance, please refer to the General Maintenance sheet.

The Tidalstone™ Flooring System should be inspected for wear every 2 to 4 years. The system should be resealed with the appropriate Westcoat topcoat every 3 to 5 years depending upon traffic and UV exposure. Contact the original Installer of Westcoat for complete re-coating instructions.

Health Precautions

Inhalation of vapor or mist can cause headache, nausea, irritation of nose, throat and lungs. Avoid breathing vapors. It is strongly recommended that respirators are worn. Prolonged or repeated skin contact can cause slight skin irritation. All epoxies have the potential of causing skin irritations or allergic reactions. Be careful not to get on skin, clothes or in eyes. Gloves are strongly recommended. If splashed in the eye, flush with warm water and contact a physician if blurring persists.

Solvent based products are extremely flammable. Extinguish all pilot lights and sources of ignition, such as electrical motors. Be sure to have adequate cross ventilation prior to installing.

Limitations


- This system is designed for professional use only.
- Read Product Specification Sheets for every product you will be using before beginning the project.
- Be sure to do adequate surface preparation.
- It is recommended to produce a mock up prior to proceeding with this project.
- Ensure that the EC-102 and TC-62 Broadcast Coat is dry enough, before sanding. Avoid aggressive sanding as this may damage the surface.
- Be sure to measure and mix properly.
- For interior use only.
- Test for moisture in concrete and vapor drive.
- Be aware of the pot life of mixed material.
- Do not apply in temperatures below 50°F or temperatures above 90°F. Cooler temperatures will cause slower dry times.
- Thinly applied coatings may not hide epoxy patches, rough concrete or shotblast tracks.
- Heavier topcoat may become slippery.
- Approval and verification of proposed colors, textures and slip resistance is recommended.
- Do not allow Westcoat products to freeze.

Slip Precaution

Westcoat Specialty Coatings Systems highly recommends the use of a slip-resistant additive to all coatings/systems that may be exposed to wet, oily, greasy or slippery conditions. It is the end user's responsibility to provide a flooring system that meets current safety standards. Westcoat and its distributors will not be responsible for injury incurred during a slip and fall incident. For the current coefficient of friction requirements, please consult your local building codes.

DISCLAIMER: PURCHASER'S SOLE AND EXCLUSIVE REMEDY AGAINST THE MANUFACTURER OF WESTCOAT, SHALL BE LIMITED SOLELY TO THE REPLACEMENT OF ANY DEFECTIVE MATERIAL OR A PAYMENT BY THE MANUFACTURER IN AN AMOUNT EQUAL TO THE COST OF THE ORIGINAL MATERIAL.





westcoat®

**SYSTEM
SPECIFICATION**

EC

EPOXY COAT
DURABLE RESINS & HARDENERS

Tidalstone™ Flooring System Thin Film

Technical Data

Chemical Resistance

SC-65F Water-Based Flat Polyurethane Sealer

Chemical Resistance

Muriatic Acid (31.5% HCL)	5
Sulfuric Acid (50% H2SO4)	5
Sulfuric Acid (93% H2SO4)	1
Nitric Acid (10% HNO3)	5
Sodium Hydroxide (50% NaOH)	5
Isopropyl Alcohol (99%)	4
Bleach (sodium hypochlorite)	5
Vinegar (3-5% acetic acid)	5
Transmission Fluid	5
Gasoline	5
Brake Fluid	5
409 Surface Cleaner	5
Pine Sol Solution	5
Blood & Body Fluids	5
Iodine Solution	5
Mustard	5/5s
Ketchup	5/5
Red Wine	5/5
Acetone	5
Methyl Ethyl Ketone (MEK)	5
Xylene	5
Skydrol	5
Ethanol	5
Methanol	5

Key:

5 = Best (no effect)

4 = Softens (recovers)

3 = Softens (no recovery)

2 = Blistered (no recovery)

1 = Worst (destroyed)

s = Stains but resists degradation

Testing done per ASTM D1308

All Single Numbers = 2 hr Contact time

All Multiple Numbers Separated by a Slash = 2 hr contact time / 24 hr contact time

DISCLAIMER: PURCHASER'S SOLE AND EXCLUSIVE REMEDY AGAINST THE MANUFACTURER OF WESTCOAT, SHALL BE LIMITED SOLELY TO THE REPLACEMENT OF ANY DEFECTIVE MATERIAL OR A PAYMENT BY THE MANUFACTURER IN AN AMOUNT EQUAL TO THE COST OF THE ORIGINAL MATERIAL.



westcoat®

4007 Lockridge St • San Diego, CA 92102
800-250-4519 • Fax 619-255-7187 • westcoat.com

5 of 5
Tidalstone™ Thin Film 11/25



westcoat®

CSI SPECIFICATION



**SECTION 09 67 23 RESINOUS FLOORING
TIDALSTONE FLOORING SYSTEM – THIN FILM**

PART 1 GENERAL

1.01 SUMMARY

- A. Section includes: Provide a complete resinous flooring system for concrete surfaces that meet the requirements for specific use indicated in the contract documents. Include all applicable substrate testing, surface preparation, and detail work.

1.02 RELATED SECTIONS

- A. Section 033000 – Cast-In-Place Concrete
- B. Section 090000 – Finishes

1.03 SUBMITTALS

- A. Submit under provisions of Section 013300.
- B. Product Data: Submit manufacturer's product data sheets on each product and system to be used including:
 - 1. Preparation instructions and recommendations.
 - 2. Storage and handling requirements.
 - 3. Installation methods.
 - 4. Maintenance requirements.
- C. Selection Samples: For each system specified, provide two sets of samples and color charts, representing manufacturer's full range of colors and patterns.

1.04 QUALITY ASSURANCE

- A. All materials used in the Tidalstone Flooring System – Thin Film shall be manufactured and provided by a single manufacturer to ensure compatibility and proper bonding.
- B. Use adequate numbers of skilled workmen thoroughly trained and experienced in the necessary crafts and completely familiar with the specified requirements and methods needed for proper performance of the work of this section.
- C. Contractor shall have a minimum of 3 years experience installing epoxy floor coatings similar to that which is required for this project and who is acceptable to the manufacturer.
 - 1. Applicator shall designate a single individual as project foreman who shall be on site at all times during installation.
 - 2. Contractor must show and have QCA Qualified Contractor/Applicator paperwork from the manufacturer of the coating system, as required to obtain a long-term jobsite specific warranty.
- D. Convene a pre-application meeting before the start of application of coating system. Require attendance of parties directly affecting work of this section, including: Architect, contractor, applicator, and authorized representative of the coating system manufacturer and interfacing trades. Review the following:
 - 1. Drawings and specifications affecting work of this section.
 - 2. Protection of adjacent surfaces.
 - 3. Surface preparation and substrate conditions.
 - 4. Application.
 - 5. Field quality control.
 - 6. Protection of coating system.
 - 7. Repair of coating system.
 - 8. Coordination with other work.

1.05 DELIVERY, STORAGE & HANDLING

- A. Delivery: Materials shall be delivered to the job site in sealed, undamaged containers. Each container shall be clearly marked with manufacturer's label showing type of material, color, and lot number.
- B. Storage: Store all materials in a clean, dry place with a temperature range in accordance with manufacturer's instructions.
- C. Handling: Handle products carefully to avoid damage to the containers. Read all labels and Material Safety Data Sheets prior to use.

1.06 PROJECT SITE CONDITIONS

- A. Maintain environmental conditions (temperature, humidity, and ventilation) within the limits recommended by the manufacturer.
- B. All concrete should be tested for moisture before applying a seamless coating. If moisture emissions exceed 5 lbs/1000 square feet (ASTM F1869) or if the relative humidity (RH) exceeds 75% (ASTM F2170), see EC-15 Moisture Vapor Barrier product specification.
- C. Concrete must be at least 2500 psi.
- D. Concrete must be cured for a minimum of 28 days before coating is applied.
- E. Schedule coating work to avoid excessive dust and airborne contaminants. Protect work areas from excessive dust and airborne contaminants during coating application.
- F. Before any work is started, the applicator shall examine all surfaces for any deficiencies. Should any deficiencies exist, the architect, owner or general contractor shall be notified in writing and any corrections necessary shall be made.

1.07 WARRANTY

- A. Upon completion of the work in this section provide a written warranty from the manufacturer against defects of materials for a period of 1 (one) year. To obtain project specific warranty the coating system applicator must be a Westcoat Qualified Contractor/ Applicator and apply for warranty.

PART 2 PRODUCTS

2.01 MANUFACTURERS

- A. Acceptable manufacturer: Westcoat Specialty Coatings; 4007 Lockridge Street, San Diego, CA 92102. Telephone 800-250-4519. Fax 619-255-7187. Website: www.westcoat.com.

2.02 MATERIALS

- A. As basis of design Westcoat Tidalstone Flooring System – Thin Film (no substitutions will be accepted): Resinous flooring system with EC-12 Epoxy Primer, TC-62 Tidalstone Aggregate blends, EC-102 Polyaspartic Topcoat and SC-65F Sealer.

2.03 COMPONENTS

- A. Tidalstone Flooring System – Thin Film:
 - 1. Primer: EC-12 Epoxy Primer 250-300 square feet per gallon.
 - 2. Broadcast Coat: EC-102 Polyaspartic (pigmented) 175-225 square feet per gallon.
 - 3. Color Chip Broadcast: TC-62 Tidalstone Aggregate Blends into the wet EC-102 at a rate of 7-8 square feet per pound.
 - 4. Polyaspartic Topcoat: EC-102 Polyaspartic. 1st coat applied at 120-140 square feet per gallon. 2nd coat applied at 250-300
 - 5. WB Polyurethane: SC-65F WB Flat Polyurethane Sealer. Two coats applied at 680-720 sq. ft. per gallon with CA-33 Aluminum Oxide #320 (2-4 oz per gal of SC-65F).

2.04 ACCESSORIES

A. Supplemental Materials:

1. Patching materials shall be EC-72 Epoxy Patch Gel.
2. Optional skid resistance aggregate shall be CA-29, CA-30, CA-31 Safe Grip or CA-33 Aluminum Oxide to meet the owners skid resistance requirements.
3. Optional cove base shall be Westcoat's Epoxy Cove System.
4. Westcoat's Flex Epoxy system may be used under the Tidalstone Thin Film system, when a 100% solids flexible epoxy membrane is required.

Optional Topcoats:

4. SC-65G WB Gloss Polyurethane may be used in lieu of SC-65F when a low odor, solvent free, mar and chemical/UV resistant gloss finish is required.
5. SC-65SG WB Semi-Gloss Polyurethane may be used in lieu of SC-65F when a low odor, solvent free, mar and chemical/UV resistant semi-gloss finish is required.
6. EC-95G Gloss Polyurethane may be used in lieu of SC-65F when a chemical/UV resistant, solvent-based gloss finish is required.
7. EC-95F Flat Polyurethane may be used in lieu of SC-65F when a chemical/UV resistant, solvent-based flat finish is required.
8. EC-101 Polyaspartic 100% Solids may be used in lieu of EC-102 as a high gloss, quick drying, high build, mar and chemical resistant finish with outstanding wear resistance.
9. EC-36 may be used in lieu of EC-102 when a 100% solids epoxy is required.

PART 3 EXECUTION

3.01 EXAMINATION

A. Verification of Conditions.

1. Inspect all surfaces to receive epoxy flooring. The surface must be structurally sound, clean, dry and free of grease, paint, oil, dust, curing agents, laitance or any foreign material that will prevent proper adhesion.
2. Conduct calcium chloride testing according to ASTM F1869.
4. Before starting work, report in writing to the authority having jurisdiction any unsatisfactory conditions.

3.02 SURFACE PREPARATION

- A. Prepare surfaces using methods recommended by the manufacturer for achieving the best result for the substrate under the project conditions.
- B. Shot blast or mechanically abrade the surface to achieve a surface profile equal to CSP 3 as specified by ICRI.
- C. Clean Surfaces thoroughly prior to installation.
- D. Rout and clean moving cracks and joints: fill with manufacturer's recommended flexible epoxy filler material.
- E. Repair any non-moving surface deviations with manufacturer's recommended patching material.

3.03 INSTALLATION

- A. Install coatings in accordance with manufacturer's instructions.
- B. Mix multi-component materials in accordance with manufacturer's instructions.
- C. Use application equipment, tools, and techniques in accordance with manufacturer's instructions.
- D. Uniformly apply coatings at spread rates and in number of coats to achieve specified mil thickness recommended by the manufacturer.
 1. Install integral cove base where indicated on the contract drawings and according to manufacturer's instructions.
 2. Key in all drains, edges, and transition points according to manufacturer's instructions.

- E. Broadcast aggregates in accordance with the specified system and manufacturer's instructions.
- F. Adhere to all limitations, instructions, and cautions for epoxy coating as stated in the manufacturer's published literature.

3.04 FIELD QUALITY CONTROL

- A. Verify coatings and other materials are as specified.
- B. Verify coverages of the system as work progresses. Areas found not to meet the required thickness shall receive additional material until specified thickness is attained.
- C. Manufacturer's representative shall provide technical assistance and guidance for surface preparation and application of coating systems.

3.05 PROTECTION AND CLEAN-UP


- A. Prohibit traffic on floor for 48 hours after installation. Avoid heavy abrasion and chemical exposure for 5 days. Allow 72 hours minimum for vehicular traffic.
- B. Protect finished surfaces of coating system from damage during construction.
- C. Touch-up, repair or replace damaged flooring system after substantial completion.
- D. Clean area and remove all debris upon completion of work. Dispose of empty containers properly according to current Local, State and Federal regulations.

3.06 MAINTENANCE

- A. Contractor shall provide to owner, maintenance and cleaning instructions for the floor system upon completion of work. Owner is required to clean and maintain the surfaces to maintain manufacturer's warranty.

END OF SECTION

This guide specification has been prepared by Westcoat Specialty Coating Systems to assist design professionals in developing a project specific specification. This guide is a template that must be reviewed and adapted by specifiers to comply with project requirements. This guide specification is not to be copied directly into a project specification manual without review.



westcoat®


COLOR CHART



westcoat


**TC-62 TIDALSTONE
AGGREGATE BLENDS**

Cambria | 180




Over Black

Avalon | 182




Over Cape Cod Gray

Malibu | 187




Over Deep Tan

Mendocino | 183




Over Stone Gray

Laguna | 184




Over Cape Cod Gray

Hermosa | 185



Over White

Solana | 188



Over Concrete Gray

Coronado | 186



Over Deep Tan

Trinidad | 181



Over Travatan



CAUTION:


Color will vary between products and sheens. This chart is for reference only. Please request an actual color sample and apply sample on site before beginning any project.





westcoat®

SAMPLE WARRANTY



westcoat[®]
SPECIALTY COATING SYSTEMS

WARRANTY

WESTCOAT TIDALSTONE™ THIN FILM MATERIAL WARRANTY

Subject to the conditions, limitations and requirements set forth below, Westcoat warrants the Westcoat TIDALSTONE™ materials to be free of defects in the material for a period of one (1) year from the date of original purchase of the materials provided that the materials are installed by a professional applicator with experience installing the Westcoat TIDALSTONE™ subject to all terms and conditions set forth below.

If the Westcoat TIDALSTONE™ materials fail due to defects within the warranty period, Westcoat, in its sole discretion, will either provide replacement materials for the defective TIDALSTONE™ materials or reimburse the original purchaser in an amount not to exceed the original cost of the materials. Westcoat shall in no way be responsible or liable for any labor costs or any incidental or consequential damages, including without limitation, economic losses, lost profits, business interruption, loss of use, contribution, indemnity or other losses arising from the use of the TIDALSTONE™ materials.

This warranty is limited to the original purchases and is non-transferable. This warranty is void if the TIDALSTONE™ materials are: not properly maintained; not installed pursuant to the current system information sheet; and/or applied at any area that is not built in accordance with applicable building codes. The warranty is also void if all of the materials are not purchased from an authorized distributor of Westcoat.

This warranty does not apply to and Westcoat has no responsibility or liability for: (1) the condition or movement of the substrate; (2) moisture rising from substrate and/or efflorescence; (3) the loss of gloss, fading or cleaning; (4) repairs and/or maintenance of the sealer and texture coat (5) waterproofing of any sort; (6) abuse or misuse of the materials; or (7) improper installation; or (8) surfaces less than 2,500 psi concrete.

THIS MATERIAL WARRANTY AND THE REMEDIES PROVIDED HEREUNDER ARE EXCLUSIVE AND GIVEN IN LIEU OF ALL OTHER WARRANTIES (WHETHER WRITTEN, ORAL, IMPLIED OR STATUTORY). THERE ARE NO OTHER WARRANTIES, EITHER EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, THAT EXTEND BEYOND THAT SPECIFICALLY DESCRIBED HEREIN. PURCHASER'S SOLE AND EXCLUSIVE REMEDY AGAINST THE MANUFACTURERS OF WESTCOAT, INCLUDING CLAIMS BASED UPON THE MANUFACTURER'S NEGLIGENCE OR STRICT LIABILITY, SHALL BE LIMITED SOLELY TO THE REPLACEMENT OF ANY DEFECTIVE TIDALSTONE™ MATERIAL OR A PAYMENT BY THE MANUFACTURER IN AN AMOUNT EQUAL TO THE COST OF THE ORIGINAL TIDALSTONE™ MATERIAL.

The Westcoat TIDALSTONE™ system requires a maintenance topcoat as specified every two to four years (depending on ultraviolet exposure and/or traffic) as determined by a Westcoat QCA, licensed contractor or design professional. Inspections are required one year after installation and every two years thereafter by a Westcoat QCA, licensed contractor or design professional. The record of the inspection must be kept in writing and entitlement to the benefits of this warranty require the purchaser to show proof of purchase of the materials and the record of inspection(s).

All claims arising from any defect in the TIDALSTONE™ materials or under this Warranty shall be made, in writing, to Westcoat within ninety (90) days of the discovery of the alleged defect and within the time period of this warranty. Upon notification, Westcoat shall have the right to inspect and determine course of repair. The absence of a written claim within this time period shall constitute a waiver of all claims, rights and damages against Westcoat, and its affiliates. This warranty shall not toll or extend any statute of limitation applicable to a claim of negligence, breach of contract or strict liability against Westcoat.

Any and all disputes, claims or damages arising out of the use of TIDALSTONE™ materials or this Warranty shall be arbitrated in the County of San Diego, State of California, utilizing the services of a neutral dispute resolution service upon which the purchaser and Westcoat agree, or if they cannot agree, utilizing the services of the American Arbitration Association. The purchaser and Westcoat hereby waive any right they may have to have a jury decide any dispute.



westcoat[™]

4007 Lockridge Street San Diego, CA 92102
800 • 250 • 4519 • Fax 619 • 262 • 8606 • westcoat.com



westcoat®

GENERAL MAINTENANCE



westcoat[®]
SPECIALTY COATING SYSTEMS

**CARE &
MAINTENANCE**

INTERIOR COATINGS

Westcoat interior coating systems (including such systems as: Thin Film, Grind and Seal, Dubro Quartz, etc.) offer durable, high-performance, long lasting surfaces, that are designed to provide years of service against normal wear and usage. Seamless flooring allows for greater ease of cleaning, compared to traditional resilient flooring, due to the absence of cracks, seams and crevices that can trap dirt and contaminants. To extend the service life of your Westcoat system, it is recommended to implement a routine cleaning regimen and have periodic inspections. This information is a basic guideline only.

Routine Cleaning

All coating systems require maintenance and upkeep to ensure continued performance and to maximize the life of the system. Maintenance methods may vary depending on the system, texture, topcoat or sealer, environment conditions, slope, drainage, volume and type of traffic, and use of space.

Ensure that the coating surface is free from debris, such as sand, gravel, metals, or other abrasives that can result in premature wear of the topcoat or sealer. Grease, oils, and other contaminants should be removed promptly to maintain the surface. Establish a routine maintenance schedule for all flooring systems. Be sure to test all cleaning agents in an unnoticeable area to ensure compatibility. Refer to the manufacturer's instructions and dilution rates for all cleaning agents. Routine cleaning can be achieved by using a mild cleaning solution, such as "Simple Green", neutral pH detergent or soap. Be sure to use clean mops and change out cleaning solution regularly. Utilize a brush, broom or mechanical scrubber to help agitate and loosen up dirt and debris, especially on textured floors. Ensure that the surface is rinsed with clean water thoroughly. Do not allow cleaning agents to dry on the surface. Buildup of residue or other foreign elements can make cleaning more difficult and can also negatively affect the slip resistance of the surface.

Floor auto-scrubbing machines can be used for larger areas. Avoid using abrasive pads or brushes and use long, soft brushes. Do not allow buildup of residue or other foreign materials, as this can result in a surface that is slippery when wet. Do not use metal-based or coarse brushes, as they may damage the surface.

Wax and Floor Finishes

Westcoat interior coating systems do not typically require a wax or a floor finish material. That said, in some cases where heavy traffic is present or where you may desire to enhance the finish, a standard, commercial floor finish, that is intended for use with resinous materials can be applied. Prior to application, ensure that the surface is clean and free from any debris or wax. Apply and maintain wax or floor finish per the manufacturer's guidelines. Wax or floor finishes will need to be completely removed prior to reseal application.



westcoat[®]

4007 Lockridge St • San Diego, CA 92102
800-250-4519 • Fax 619-255-7187 • westcoat.com

1 of 2
General Maintenance INT 8/24



westcoat®
SPECIALTY COATING SYSTEMS

**CARE &
MAINTENANCE**

INTERIOR COATINGS

Maintenance and Inspections

All interior coating systems should be periodically inspected and regularly maintained by a Westcoat Qualified Contractor Applicator (QCA). Inspections are required one year after installation and every two years thereafter by a factory authorized representative. After 3-5 years, a "reseal" (thorough cleaning and reapplication of Westcoat topcoat/sealer) may be required. Existing sealer or coating should be abraded and wiped with solvent, before application of topcoat or sealer. Some topcoats and sealers may require additional preparation, prior to recoating. Should damage occur, be sure to contact the original Westcoat applicator to inspect and repair the coating system immediately.

Best Practices

- Do not expose the coating surface to traffic, moisture or chemical agents until system is fully cured.
- Immediately clean up and rinse off any chemical solutions that may stain or damage the surface.
- Do not subject the floor coating system to chemicals that it is not compatible or resistant to.
- Avoid dragging metal, concrete, pallets or other types of objects with sharp edges across the floor.
- Rolling loads with steel casters can potentially damage the surface and should be avoided.
- Avoid ponding or standing water, by ensuring that positive drainage is present before applying the floor coating system.
- Water should not be allowed to enter the flooring systems through penetrations, joints or edges.
- Furniture should have protective coasters or pads to prevent from indentations or damage.
- Tape and other adhesives should not be applied to finished floors, as this may damage the surface.

Any information provided by Westcoat Specialty Coating Systems is for general purposes only. Nothing presented by Westcoat Specialty Coating Systems constitutes design advice or a recommendation specific to a particular situation. Westcoat Specialty Coating Systems directs you to consult with the appropriate qualified design professional to ensure any product or information meets the requirements for the specific intended use, and complies with all building plans, specifications, codes or regulations. Westcoat Specialty Coating Systems expressly and specifically disclaims responsibility for any damages arising from the use of any information, and each recipient of this information agrees that there is no express or implied warranty, including any implied warranty of merchantability or fitness for a particular purpose, arising from any information provided by Westcoat Specialty Coating Systems.



4007 Lockridge St • San Diego, CA 92102
800-250-4519 • Fax 619-255-7187 • westcoat.com

2 of 2
General Maintenance INT 8/24